

**MATERIAL SAFETY DATA SHEET**

**MSDS NUMBER: ZLPBC**

**Rev. 11/02**

**24 HOUR EMERGENCY NUMBER: CHEMTREC 1-800-424-9300**

**PRODUCT: PERFORMANCE BUILDER**

**CAS NUMBER: 68515-73-1**

**FORMULATOR:**

EnviroSpec (a division of Hi-Tech Jetting Technologies, Inc.)

751 Martin Luther King Highway

Homerville, Georgia 31634

(912) 487-1778

**SECTION I – NON-HAZARDIOUS INGREDIENTS**

NONE

**SECTION II – HAZARDOUS INGREDIENTS**

<b>Chemical Name ACCIH TLV</b>	<b>%WT</b>	<b>OSHA PEL</b>	
ALKYL POLYGLYCOSIDE	25	N/A	N/A

**SECTION III – HEALTH HAZARD DATA**

**Effects of Over Exposure:**

Ingestion: None Established  
Eyes: Causes Eye Irritation  
Skin: None Established  
Inhalation: None Established

**Emergency First Aid Procedures:**

Inhalation: Move to fresh air. If illness or irritation occurs, call Physician.

Eyes: Flush with copious amounts of water until all material is removed.

If pain or irritation arises, contact Physician.

Skin: Wash exposed area with soap and water. If irritation occurs, contact Physician.

Ingestion: Contact Physician Immediately

**SECTION IV; FIRE AND EXPLOSTION HAZARD**

<b>Flash Point:</b>	None
<b>Flammable Limits:</b>	None
<b>Extinguish Media:</b>	N/A
<b>Special Firefighting Procedures:</b>	None
<b>Unusual Fire &amp; Explosion:</b>	None

**SECTION V: REACTIVITY DATA**

<b>Conditions Causing Instability:</b>	None
<b>Incompatibility:</b>	None
<b>Haz Decomposition Products:</b>	None

**SECTION VI: PHYSICAL DATA**

<b>Boiling Point:</b>	212 degrees F
<b>Specific Gravity:</b>	1.28
<b>Freezing Point:</b>	20 degrees F
<b>Vapor Density:</b>	N/A
<b>Water Solubility, %:</b>	100
<b>Vapor Pressure:</b>	N/A
<b>Appearance:</b>	Dark Brown
<b>Odor:</b>	Ammonia

**SECTION VII; SPECIAL PROTECTION INFORMATION:**

<b>Respiratory:</b> Required	No Special Equipment
<b>Ventilation:</b>	Fresh Air
<b>Eye Protection:</b> Recommended	Goggles/Safety Eyewear
<b>Protective Gloves:</b>	Recommended

**SECTION VIII: PRECAUTIONS FOR SAFE HANDLING**

**Storage and Handling:**

- Protect against Temp below 20 degrees F. At temperatures below 65 degrees F, product may begin to crystallize. Crystals will go back into solution by re-heating.

**SECTION IX: SPILL, LEAK AND DISPOSAL PROCEDURES**

**Steps to be taken in Case Material is Released or Spilled:**

- Dike area and soak up with absorbent material. Wash area with water. Dispose of absorbent material in appropriate waste container. If material is released into the environment, user should determine whether release should be reported to the appropriate state or federal authorities.

**Government Regulations:**

- None Known